



Product Information

12701 S. Ridgeway Ave
Alsip, IL 60803 USA

Telephone: +1 708-293-7750
Fax: +1 708-293-7765

Web site: www.daubertcromwell.com
E-mail: info@daubertcromwell.com

Removal of Nox-Rust® 3100/3100G Liquids

Nox-Rust 3100 and 3100G are wax-based, solvent-type, cold applied, corrosion preventive liquids designed for use on ferrous and non-ferrous metals in indoor or outdoor storage conditions. They deposit a transparent, firm, wax-like film onto metal surfaces that is removable with most solvent borne thinners, by vapor degreasing, high pressure hot alkaline wash or using low pressure steam. The most common method is to use a high pressure (1200 PSI+) hot (160-180°F, 71-82°C) with a pH of 11 or higher, followed by a water rinse.

Note that the coating cures in the first 24 hours after application, and the self-healing properties will continue to be evident for approximately 90 days. As the products age, the film will become firmer.

Caution should be taken to avoid use of chlorinated or highly aromatic solvents when removing from painted surfaces, as these solvents may adversely affect the paint.

For further information and specific application assistance, consult the Daubert Cromwell Product Manager-Liquids or your local sales representative; 1-800-535-3535; info@daubertcromwell.com.

® Registered trademark of Daubert Cromwell

©2015

The data, statements and recommendations in this product information sheet are based on testing, research and other development work, which has been carefully conducted by us, and we believe such data, statements and recommendations will serve as reliable guidelines. Physical properties shown herein represent typical values and are not intended for use in writing specifications. However, this product is subject to numerous uses under varying conditions over which we have no control, and accordingly, we do NOT warrant that this product is suitable for any particular use. Users are advised to test the product in advance to make certain it is suitable for their particular production conditions and use. All products manufactured by us are warranted to be first class material and free from defects in material and workmanship. Liability under this warranty is limited to the net purchase price of any such products proven defective or, at our option, to the repair or replacement of said products upon their return to us transportation prepaid. All claims on defective products must be made in writing within 30 days after the receipt of such products in your plant and prior to further processing or combining with other material and products.

WE MAKE NO WARRANTY, EXPRESS OR IMPLIED, AS TO THE SUITABILITY OF ANY OF OUR PRODUCTS FOR ANY PARTICULAR USE, AND WE SHALL NOT BE SUBJECT TO LIABILITY FROM ANY DAMAGES RESULTING FROM THEIR USE IN OPERATIONS NOT UNDER OUR DIRECT CONTROL.

THIS WARRANTY IS EXCLUSIVE OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, AND NO REPRESENTATIVE OF OURS OR ANY OTHER PERSON IS AUTHORIZED TO ASSUME FOR US ANY OTHER LIABILITY IN CONNECTION WITH THE SALE OF OUR PRODUCTS.